

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁵: A61L 27/00	A1	(11) International Publication Number: WO 94/13334 (43) International Publication Date: 23 June 1994 (23.06.94)
(21) International Application Number: PCT/SE93/01032 (22) International Filing Date: 1 December 1993 (01.12.93) (30) Priority Data: 924697 4 December 1992 (04.12.92) NO (71) Applicant (for all designated States except US): AKTIEBOLAGET ASTRA [SE/SE]; S-151 85 Södertälje (SE). (72) Inventors; and (75) Inventors/Applicants (for US only): ELLINGSEN, Jan, Eirik [NO/NO]; Ekeberglia 14, N-1340 Bekkestua (NO). RØLLA, Gunnar [NO/NO]; Bygdø Allé 56 A, N-0265 Oslo (NO). (74) Agent: LINDEROTH, Margareta; Aktiebolaget Astra, Patent Dept., S-151 85 Södertälje (SE).		(81) Designated States: AT, AU, BB, BG, BR, BY, CA, CH, CZ, DE, DK, ES, FI, GB, HU, JP, KP, KR, KZ, LK, LU, MG, MN, MW, NL, NO, NZ, PL, PT, RO, RU, SD, SE, SK, UA, US, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>
(54) Title: PROCESS FOR TREATING A METALLIC SURGICAL IMPLANT (57) Abstract Metallic surgical implant materials having improved strength of connection with bone are produced when the implants are treated prior to implantation with an aqueous solution of sodium fluoride.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

PROCESS FOR TREATING A METALLIC SURGICAL IMPLANT

5 This invention relates to a process for treating a metallic surgical implant, particularly an implant made of titanium or a titanium alloy.

Background of the Invention

10 Titanium and titanium alloys are frequently used as implant materials in dental and orthopedic surgery because of their good compatibility with bone tissue and their tendency to form a firm attachment directly with bone tissue. The interaction between bone tissue and metal, leading to such firm attachment, was coined "osseointegration" by Brånemark and co-workers, of Gothenburg, Sweden, in the late 1970's, but the mechanics of the attachment process are not yet fully
15 understood.

The standard surgical technique for fixing a surgical implant involves a two-stage process. In the first stage the soft tissue covering the bone tissue is opened and a base part of the implant is placed in the bone tissue. The soft tissue is closed and
20 the implant left to osseointegrate for a comparatively long period of time. In the second stage the soft tissue is re-opened and the load-bearing parts of the implant are attached to the base part. A two-stage technique such as this has some disadvantages, since the long period needed for osseointegration is very uncomfortable for the patient. Furthermore, in orthopaedics it is preferable to have
25 a one-stage operation since a joint, for example the hip joint, should not be operated on twice if this can be avoided. One prerequisite of a one-stage operation is that the time needed to obtain sufficient strength at the bone tissue -implant interface, is short. In addition, there may be problems in obtaining a full osseointegration in those cases where the quality of the bone is poor or the
30 available space is limited, for example in the upper jaw or in the posterior parts of

the lower jaw above the nerve. In these places it would therefore be desirable to stimulate the regeneration of the bone tissue around the implant.

5 There are to date several methods for treating implants made of titanium in order to obtain a better attachment of the implant. Some of these involve altering the topography of the implant, for example by creating relatively large irregularities on the implant surface in order to obtain a better mechanical retention and to increase the area of attachment, by for example plasma spraying, blasting or etching. Although the retention may be improved, the time necessary for the
10 osseointegration process may be longer since the bone tissue would have to grow into the irregularities in the surface.

Other methods involve altering of the chemical properties of the implant surface. For example one such method involves the application of a layer of ceramic
15 material such as hydroxyapatite to the implant surface, inter alia in order to stimulate the regeneration of the bone tissue. Ceramic coatings however may be brittle and may flake or break off from the implant surface, which may in turn lead to the ultimate failure of the implant.

20 US Patent No. 4,330,891 could perhaps be said to combine each of the above, in that the provision of an element with a micro-pitted surface which micro-pits are within a certain diameter range, is said to effect improved properties as regards acceptance of the carrier element, and primarily improved durability of the healthy ingrowth of the element due to its biological quality.

25

The Invention

It is the object of the present invention to provide a metallic surgical implant having improved strength of connection with bone. This object is achieved by treating a metallic surgical implant with a solution of sodium fluoride according to
30 the present invention.

According to the present invention, therefore, there is provided a process for treating a metallic surgical implant prior to implantation, comprising treating the said implant with an aqueous solution containing a soluble fluoride salt, which solution is of pH 2.5 to pH 6.

5

Preferably, the aqueous solution is of pH 2.5 to pH 5.

The present invention is particularly of interest in the treatment of titanium or titanium alloy, such as Ti/Al/V alloy, implants, but may also be employed for the treatment of other metallic implants such as those of zirconium and tantalum, and coated metallic implants such as hydroxyapatite-coated titanium.

10

The treatment solution preferably contains sodium fluoride in a concentration of 0.1% to saturated, such as 0.4% to saturated, or 0.5% to saturated. Most preferably the sodium fluoride is present in substantially saturated amount at room temperature, such as 4% at room temperature.

15

Treatment of the metallic surgical implant may be carried out in any suitable manner, for example by immersing the implant in the treatment solution for a period of time and with or without agitation. Varying temperatures may be employed; parameters such as temperature and time may be selected according to the concentration of the treatment solution and the other process parameters. In most cases, for treatments at room temperature, treatment should be carried out for at least ten seconds such as from ten seconds to sixty minutes; in the case of a saturated solution of fluoride, treatment at room temperature for around five minutes is preferable. Treatment is conveniently carried out at standard pressure, but elevated pressures may be used where desired. Preferably, treatment is carried out at standard pressure and temperature.

20

25

The treatment solution of the present invention may be simply prepared, by

30

dissolving the appropriate amount of sodium fluoride in water. The pH may be lowered by small additions of acid, such as HF or HCl, and if required small amounts of base may be added to raise the pH.

- 5 Prior to treatment, the implant material may be cleaned by standard techniques such as are well known in the art.

After treatment, the implant material may be washed in distilled water and kept under sterile conditions.

10

- In titanium implants treated according to the present invention, a force four times greater than that needed to displace untreated implants, was required in order to displace the said implants from bone. The implants tested were conical in shape such that mechanical and frictional influences were minimised. It is believed that the improved properties found in implants treated according to the present invention are the result of improved biocompatibility and osseointegration resultant from the treatment process. While we do not wish to be limited to the expression of theories herein, the improved biocompatibility is thought to be due, at least in part, to fluoride being retained on the surface of the treated implant.

15
20

The invention will now be illustrated by Example.

Examples

25 Comparative Example

- Six surgical implants, of commercially pure (c.p.) titanium, 5 mm in length and generally conical in shape having a diameter at one end of 3 mm and at the other end 2 mm, were prepared by machining using a "Maximat super 11" (TM) turning lathe. Therefore the area of the conical sides of the implant, i.e. the part of the implant to be located in the bone, is 39 mm².

30

Each implant was cleaned according to a well-known cleaning procedure involving the following steps:

1. Treatment with trichloroethylene with ultrasonic treatment, for 15 minutes.
- 5 2. Rinsing in absolute ethanol, for 10 seconds.
3. Three successive treatments with ethanol with ultrasonic treatment, each for 10 minutes.

Each cleaned implant was sterile packaged in a Mediplast (TM) sterile envelope, and autoclaved in a Citomat 162 (TM) (LIC Company) autoclave, at 120°C for 30
10 minutes.

Example 1

A sodium fluoride bath was prepared simply by dissolving sodium fluoride crystals in distilled water, to give a 4% solution. The pH of the bath was adjusted to pH
15 3.7 with 6N hydrochloric acid.

Six implants, prepared, cleaned, sterile packaged and autoclaved exactly as in the Comparative Example above, were removed from their sterile packages, placed in the sodium fluoride treatment bath and left there for ten minutes. Thereafter each
20 was washed three times in a bath of distilled water, for periods of 30 seconds each wash. After being allowed to dry at room temperature, each implant was transferred to a Mediplast (TM) sterile envelope to await surgical implantation.

Implant study

25 Chinchilla rabbits were used as test animals. The rabbits were randomly distributed regarding sex, but all had a weight of 2.5 kg at the start of the study. Each animal was sedated by injection using a combination of fluanozonium 1.0 mg/kg and fentanylum 0.02 mg/kg (Hypnorm, Janssen Pharmaceuticals, Belgien) and locally anesthetised with xylocaine/adrenaline (AB Astra). Two cavities were
30 drilled in each rabbit's right ulna, using standardised bores designed to provide

cavities into which the conical implants would exactly fit. Implants according to the Comparative Example or Example 1 were placed in the cavities of each rabbit, using titanium tweezers so as to avoid the influence of other metals, and left for sixty days.

5

At the end of sixty days the rabbits were sacrificed by injection with pentobarbitol natrium, and the ulna's removed and placed in sterile physiological saline to await a "push-out" test the same day.

10 An Instron model 1121 tensile testing machine (Instron, U.K.) inter alia comprising a support jig and a ram adjusted for a load range of 0 - 200 N, was employed to measure the maximum force needed to separate each implant from bone. Milling tracks, to fit the support jig, were made in the specimen to be tested, in the bone surrounding the larger end of the implant, and the specimen was placed on the
15 support jig. The ram was lowered at a speed of 1 mm/min., and the maximum force required to separate the implant from the bone was recorded.

This recorded pressure gives a direct assessment of the strength of connection of the implant and bone, the higher the required force the stronger the connection.

20

The results are recorded in Table 1.

25

30

Table 1

Recorded force (N)

Implants according to
the Comparative ExamplesImplants according to
Example 1

5

1 37.0

1 105.0

2 47.5

2 121.0

3 24.5

3 100.0

4 11.5

4 118.2

10

5 28.5

5 125.0

6 16.0

6 128.0

mean 27.5

mean 116.2

15 The much greater strength of bone connection with implants treated in accordance
with the present invention is apparant from the above.

20 Histological examination demonstrated that the implants according to Example 1
were surrounded even in the ulna's spongiosa by a thick layer of newly formed
bone which was in close contact with the implants. In contrast the untreated
implants, i.e. those according to the Comparative Examples, were only partly
covered, by a thin bone layer, in the spongiosal area.

CLAIMS

1. A process for treating a metallic surgical implant prior to implantation, comprising treating said implant with an aqueous solution containing sodium fluoride, which solution is of pH 2.5 to pH 6.
2. A process according to claim 1, wherein the aqueous solution is of pH 2.5 to pH 5.
3. A process according to claim 1 or claim 2, wherein the metallic surgical implant comprises titanium or a titanium alloy.
4. A process according to claim 1, 2 or 3, wherein the concentration of the solution of sodium fluoride is in the range 0.1 % to saturated.
5. A process according to claim 4, wherein the concentration of the solution of sodium fluoride is in the range 0.4 % to saturated.
6. A process according to claim 4, wherein the solution of sodium fluoride solution is substantially saturated at room temperature.
7. A process according to claim 4, 5 or 6, wherein the concentration of the solution of sodium fluoride is approximately 4 % at room temperature.

8. A process according to any of claims 1 to 3 and 7, wherein the pH of the solution is approximately 3.7.

9. A process according to any preceeding claim, wherein said treatment
5 comprises immersing the implant in the aqueous solution at room temperature for a period of at least ten seconds.

10. A process according to any of claims 1 to 3 and 8 to 9, wherein said treatment comprises immersing the implant in the aqueous solution at room
10 temperature for ten seconds to five minutes.

11. A process according to any of claims 1 to 3 and 8 to 10, wherein said treatment comprises immersing the implant in the aqueous solution of sodium fluoride at room temperature for a period of approximately five minutes.

15

12. A metallic surgical implant treated by the process of any of claims 1 to 11.

INTERNATIONAL SEARCH REPORT

International application No.

PCT/SE 93/01032

A. CLASSIFICATION OF SUBJECT MATTER

IPC5: A61L 27/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC5: A61L, A61C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

SE,DK,FI,NO classes as above

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

CA, WPI, CLAIMS, EPODOC, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	STN International, File CA, Chemical abstracts, volume 116, no. 24, 15 June 1992 (Columbus, Ohio, US), Nishino, Toshiharu: "Experimental study on hydroxyapatite soaked in sodium fluoride", abstract no. 241877k, & Nippon Seikeigeka Gakkai Zasshi, 65(12), 1199-210	1-12
	--	
X	US, A, 5039546 (H. CHUNG ET AL), 13 August 1991 (13.08.91), column 2, line 56 - column 3, line 39, claims	1-12
	-- -----	

☐ Further documents are listed in the continuation of Box C.
 ☒ See patent family annex.

* Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

2 March 1994

Date of mailing of the international search report

10 -03- 1994

Name and mailing address of the ISA/
Swedish Patent Office
Box 5055, S-102 42 STOCKHOLM
Facsimile No. +46 8 666 02 86

Authorized officer

Sofia Nikolopoulou
Telephone No. +46 8 782 25 00

INTERNATIONAL SEARCH REPORT

Information on patent family members

28/01/94

International application No.

PCT/SE 93/01032

Patent document
cited in search reportPublication
datePatent family
member(s)Publication
date

US-A- 5039546

13/08/91

NONE